



Office de la Propriété
Intellectuelle
du Canada

Un organisme
d'Industrie Canada

Best Available Copy
Canadian
Intellectual Property
Office

An agency of
Industry Canada

CA 2037603 C 2005/05/17

(11)(21) 2 037 603

(12) BREVET CANADIEN
CANADIAN PATENT

(13) C

(22) Date de dépôt/Filing Date: 1991/03/06

(41) Mise à la disp. pub./Open to Public Insp.: 1992/09/02

(45) Date de délivrance/Issue Date: 2005/05/17

(30) Priorité/Priority: 1991/03/01 (663,254) US

(51) Cl. Int.⁵/Int. Cl.⁵: C09D 191/06, B01J 2/14, C09D 17/00

(72) Inventeur/Inventor:

FINDLEY, LARRY K., US


(73) Propriétaire/Owner:

EZ COLOR CORPORATION, US,

(74) Agent: MOFFAT & CO.

(54) Titre : METHODE DE PRODUCTION DE PASTILLES DE CONCENTRE DE MATIERE COLORANTE

(54) Title: METHOD OF PRODUCING PELLETIZED COLOR CONCENTRATE AND PELLETS PRODUCED THEREBY



(57) Abrégé/Abstract:

A color concentrate pellet and a method for producing same. Pigment and carrier, both in powdered form, are placed in a high intensity bowl-type mixer. Small granules are produced. These granules are cold-pressed in a pellet mill and color concentrate pellets of a conventional size and shape are produced. These pellets contain up to 90% pigment by weight, and have a melting point of less than about 230° F. The pellets are friable and are mixable and processable with commercially sized natural pellets without substantial setting out. The carrier in the pellet acts as a universal carrier. Pellets with additives in substitution for pigments are also disclosed.

Canada

<http://opic.gc.ca> • Ottawa-Hull K1A 0C9 • <http://cip0.gc.ca>

OPIC • CIP0 191

8/17/07, EAST Version: 2.1.0.14

OPIC



CIP0

2037603

METHOD OF PRODUCING PELLETIZED COLOR
CONCENTRATE AND PELLETS PRODUCED THEREBY

ABSTRACT OF THE DISCLOSURE

1
2 A color concentrate pellet and a method for produc-
3 ing same. Pigment and carrier, both in powdered form, are
4 placed in a high intensity bowl-type mixer. Small granules
5 are produced. These granules are cold-pressed in a pellet
6 mill and color concentrate pellets of a conventional size and
7 shape are produced. These pellets contain up to 90% pigment
8 by weight, and have a melting point of less than about 230°
9 F. The pellets are friable and are mixable and processable
10 with commercially sized natural resin pellets without sub-
11 stantial settling out. The carrier in the pellet acts as a
12 universal carrier. Pellets with additives in substitution
13 for pigments are also disclosed.

METHOD OF PRODUCING PELLETIZED COLOR
CONCENTRATE AND PELLETS PRODUCED THEREBY

BACKGROUND OF THE INVENTION

This invention relates generally to the coloring of plastics, and more specifically to improved color concentrate pellets and the process for making same.

Discussion of Related Art

A common method of coloring plastics is to use color concentrate pellets. A color concentrate pellet is solid and is typically comprised of pigment and carrier. The pigment colors the plastic. The carrier acts as a binder and generally also acts to "wet" the pigment so that the pigment will mix well with the resin or plastic to be colored and so that the pigment will be well dispersed throughout the final molded, extruded, cast, or otherwise formed plastic product.

In conventional color concentrate pellets, the pigment is mixed with a carrier which is a thermoplastic resin material such as polypropylene, polyethylene, ABS, or polystyrene. These materials and the pellets produced thereby have a melting point in the range of 350° to 400° F. To make these conventional color concentrate pellets, the pigment and carrier are mixed and heated to about 550° to 600° F. The mixture melts and is mixed, and is extruded through an extruder and then solidifies and is cut into conventional pellet size, a cylinder about 1/8-inch in diameter and about 1/8 to 1/4 inch in length.

These conventional color concentrate pellets contain organic and inorganic pigments, and are typically 30%

1 to 50% pigment by weight with the balance being thermoplastic
2 resin.

3 These conventional pellets are then mixed with
4 natural resin pellets of the same general size and shape to
5 effect colorization. Natural resin pellets are pellets which
6 have not yet been colored. Commercially sized natural resin
7 pellets are cylindrically shaped, are about 1/8 inch in
8 diameter, and are about 1/8 to 1/4 inch long.

9 One problem with conventional color concentrate
10 pellets is that the carrier generally must be compatible with
11 the natural resin to be colored. To be compatible, the two
12 must be the same or very similar. For example, a poly-
13 propylene carrier would be compatible with a polypropylene
14 natural resin, but would not be compatible with PVC natural
15 resin. Mixing a carrier with an incompatible natural resin
16 could adversely affect the physical properties of the final
17 molded product. The typical end product would comprise 96%
18 natural resin, 2% carrier, and 2% pigment.

19 Another problem is that the high temperatures
20 utilized in the extrusion process (550° - 600° F.) tend to
21 burn out or degrade organic pigments and certain inexpensive
22 inorganic pigments which burn out or degrade between 400° and
23 550° F.

24 The conventional process is particularly disadvan-
25 tageous with regard to organic pigments. Organic pigments
26 tend to be more heat-sensitive, more unstable, and generally
27 more expensive than inorganic pigments. The high tempera-
28 tures of the conventional process are bad for organic pig-
29 ments. These high temperatures also tend to use up a signif-
30 icant portion of the available heat history or heat tolerance
31 of the pigments and carriers utilized. These high tempera-
32 tures are thus disadvantageous.

33 Another result of the conventional process is that
34 the pellets produced are ordinarily not friable. They must

1 be melted at about 350° to 400° F. before they can be mixed
2 with natural resin.

3 The Henschel Company of Germany has, for many
4 years, manufactured a high intensity, bowl-type mixer. It
5 has been known that granules of a more or less spherical
6 shape with a diameter of about 30 to 50 microns and with a
7 pigment loading of 70% - 90% by weight could be manufactured
8 in the Henschel mixer. The granules, however, are too small
9 and do not mix well with the commercially-sized natural resin
10 pellets. They were not accepted commercially.

11 Objects of the Invention

12 It is an object of the invention to produce a color
13 concentrate pellet having a carrier that is compatible with
14 a wide range of natural resins. (Such carriers can be
15 referred to as "universal carriers" or "partially universal
16 carriers.")

17 It is a further object to produce a color concen-
18 trate pellet that can comprise up to 90% pigment, with a
19 carrier which will melt at less than about 230° F. for better
20 mixing, and will be manufactured at temperatures of less than
21 300° F. so as not to burn out or degrade certain heat-sensi-
22 tive pigments, particularly organic pigments, which have heat
23 sensitivity in the range of 400° to 550° F.

24 It is also an object of the invention to produce
25 a color concentrate pellet that is friable, will not settle
26 out upon mixing with commercially sized natural resin pel-
27 lets, will look comparable to a conventional color concen-
28 trate pellet, can be made on less expensive equipment with
29 less energy cost, and can be processed to pellet form at less
30 than 230° F. It is an object of the invention to provide a
31 process for manufacturing color concentrate pellets, particu-
32 larly those containing organic pigments, which process will

1

4

2

not unduly heat or otherwise adversely affect the qualities of organic pigments.

3

SUMMARY OF THE INVENTION

4

5

6

7

8

9

10

11

12

13

14

15

16

17

18

19

The present invention involves a process wherein color concentrate pellets of a generally conventional size and shape are formed. Pigment and carrier in powder form are placed in a high intensity bowl-type mixer. The carrier may comprise, for example, bis stearamide wax and A-C 400A* ethylene vinyl acetate. The mixer is run until small granules in the range of 10 to 50 microns in diameter are formed. These granules are then run through a standard pellet mill without supplying external heat, substantial or otherwise. This results in a pellet that has, typically, 30% to 60% to 90% pigment by weight, and which has a carrier which is compatible with a wide range of natural resins. Preferably, the pellet will contain 50% to 90% pigment by weight (including both organic and inorganic). More preferably, the pellet will contain 70 % to 90% pigment by weight and, more preferably still, the pellet will contain 80% to 90% pigment by weight. At high loading levels, energy, packaging, and shipping costs are reduced, and less carrier is used. Unfortunately, many commercial users of color concentrate pellets do not have adequate metering equipment to handle pellets with these higher loading levels, such as in the 80% to 90% range. With less accurate metering equipment, such users still prefer pellets with loading in

20

*denotes a trade-mark

1 the 50% to 75% range. When pellets have high loading levels,
2 the metering equipment must be more accurate. It is believed
3 that as users become more familiar with the benefits of
4 pellets with loading levels in the 80% to 90% range, they
5 will obtain more accurate metering equipment, and sales of
6 these more highly loaded pellets will increase. For polyvi-
7 nyl chloride siding, the pigment is frequently 100% inorganic
8 and, typically, the pellet is in the range of 45% to 75%
9 pigment by weight.

10 The pellet of the present invention will melt at
11 less than about 230° F., preferably at about or less than
12 about 200° F. The pellet is friable, and is made at a temper-
13 ature of less than 230° F., preferably at less than about
14 200° F. As a result of this low temperature of manufacture,
15 certain heat-sensitive organic pigments and certain inexpen-
16 sive heat-sensitive inorganic pigments are made available to
17 the end user. Such pigments tend to be degraded or burned
18 out at temperatures from 400° to 550° F. Thus, they would
19 be burned out or degraded if subjected to the conventional
20 extruding process, which utilizes temperatures up to 550° to
21 600° F. Most end users mold their color concentrates and
22 natural resin pellets at about 400° F.

23 The equipment utilized in the practice of the
24 present invention is less expensive than that utilized in a
25 conventional extruding line. The energy costs of the present
26 invention are about six times less than that utilized in
27 conventional extruding. The pellet produced by way of the
28 present invention is conventionally shaped and ordinarily
29 will disperse throughout the natural resin and will not
30 settle out, substantially or otherwise, when mixed and
31 processed with commercially sized natural resin pellets.

32 The fact that the pellets of the present invention
33 melt at a temperature lower than that of conventional color
34 concentrate pellets is advantageous, since they can be melted

and mixed sooner and better, and be better incorporated with the natural resin pellets. It is important that color concentrate pellet melt before the natural resin pellet for proper mixing and incorporation. Organic pigments are particularly hard to disperse. The pellets of the present invention have almost total dispersion of both organic and inorganic pigments. Streaks and color variation are effectively eliminated.

In one broad aspect then, the present invention relates to a color concentrate pellet comprising at least about 30% pigment by weight and a carrier wherein said color concentrate pellet has at least partially a geometric shape formed by a die cavity and is of a size and shape and composition such that a plurality of said color concentrate pellets are mixable and processable with commercially sized natural resin pellets to produce coloured resin without substantial settling out of said color concentrate pellets from said natural resin pellets, the carrier of said color concentrate pellet operating to bind the pigment, and wet the pigment to render it more dispersible in said natural resin, and having a melting point less than about 230°F, said pellet being cold-formed in a press in such a way that the pellet is cohesive as a result of mechanical pressure and is friable to improve its dispersibility.

In another broad aspect then, the present invention relates to a pellet for use in the plastics industry, comprising a carrier and an additive, said additive being selected from the group consisting of a slip agent, an anti-stat compound, calcium carbonate, talc, glass, ultraviolet light stabilizer and purging compound, wherein said pellet has at least partially a geometric shape formed by a die cavity and is of a size and shape such that a plurality of said pellets are mixable and processable with commercially sized natural resin pellets without substantial settling out of said pellets from said natural resin pellets, said carrier operating to bind the pigment, and wet the pigment to render it more dispersible in said natural resin, and having a melting point of less than about 230°F, said pellet being cold-formed in a press in such a way that the pellet is cohesive as a result of mechanical pressure. In a preferred form, the additive is calcium carbonate, and makes up 60% to 90% of the pellet, by weight.

In yet another broad aspect then, the present invention relates to a color concentrate pellet comprising at least 20% pigment by weight and a carrier wherein said color concentrate pellet has at least partially a geometric shape formed by a die cavity and is of a size and

6a

5 shape and composition such that a plurality of said color concentrate pellets are mixable and processable with commercially sized natural resin pellets to produce colored resin pellets, the carrier of said color concentrate pellet operating to bind the pigment, and wet the pigment to render it more dispersible in said natural resin, and having a melting point less than about 230°F, said pellet being cold-formed in a press in such a way that the pellet is cohesive as a result of mechanical pressure and is friable to improve its dispersibility, said carrier comprising siding-grade polyvinyl chloride compound.

10 BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 is a perspective view of a pellet of the present invention; and

FIG. 2 is a somewhat schematic elevational view of the die and rollers of a die-and-roller-type pellet mill.

1 The present invention disperses organic pigments
2 very well. Due to the oil absorption rate of organic pig-
3 ments, one cannot achieve as high a loading level with
4 organic pigments as one can with inorganic pigments in color
5 concentrate pellets of the present invention. One can
6 achieve up to about 40% to 42% loading levels of organic
7 pigments and up to about 90% loading levels of inorganic
8 pigments in the pellets of the present invention. (Percent-
9 ages are on a by-weight basis unless otherwise indicated.)

10 In the present invention, it is normal to use
11 combinations of organic and inorganic pigments. Typically, in
12 such a case, the organic pigment is used as a toner to give
13 vivid color, while the inorganic pigment, which tends to be
14 non-transparent, provides a more opaque color and fills up
15 the color so as to reduce transparency. Typically, high
16 levels of inorganic pigments are used in combination with
17 lower levels of organic pigments. If the loading level is
18 90% by weight, the pigment may be 100% inorganic. Alterna-
19 tively, if a loading level of 90% pigment by weight is
20 desired, up to about 40% organic pigment can be put in, with
21 the balance being inorganic pigment. If a loading level of
22 70% pigment by weight is desired, up to about 40% organic
23 pigment can be put in, with the balance being inorganic
24 pigment. If a 60% loading level is desired, this could, for
25 example, be achieved with 10% organic/50% inorganic, or 30%
26 organic/30% inorganic, or 40% organic/20% inorganic.

27 The carrier is utilized to bind the pigment and
28 also generally operates to wet the pigment so that it is more
29 dispersable in the natural resin to be colored. Bis
30 stearamide wax is a typical carrier. If dry powdered pigment
31 is incorporated directly into natural resin, there is a
32 tendency for it to form chunks and streaks, rather than to
33 uniformly color the natural resin.

1

7

2

DETAILED DESCRIPTION OF THE INVENTION

3

4

5

6

7

8

FIG. 1 illustrates a typical color concentrate pellet 10 of the present invention. The pellet is cylindrical, approximately 3/32 to 5/32 inch in diameter, preferably 4/32 inch (1/8 inch) in diameter. The length is typically about 1/8 to about 1/4 inch; preferably 1/8 inch. The 1/8-inch length size feeds better at the end user. The end 12 of the pellet typically has a broken appearance rather than a smooth knife edge or cut edge, such as may be visible on a conventionally extruded pellet.

9

10

It is difficult to characterize the pellets of the present invention on the basis of weight, since the different pigments and different carriers have different densities.

11

12

13

14

15

16

17

18

19

20

21

22

The pellet is comprised of pigment and carrier. As used in the specification and claims, pigment can include mixtures of different pigments. Pellets of the present invention typically are about 30% to about 90% pigment by weight and the balance is carrier. Organic pigments typically utilized include quinacridones and phthalocyanines and also azo-type pigments. Typical inorganic pigments include nickel titanate, titanium dioxide, carbon black, cobalt, and manganese chrome antimony titanate. Organic pigments are generally more expensive than inorganic pigments. Organic pigments tend to cost about \$14 to \$120 per pound. Inorganic pigments tend to cost about \$0.50 to \$14 per pound. Typical organic and inorganic pigments are listed in Modern Plastics Encyclopedia, Mid-October 1989 Issue, Vol. 66, No. 11, McGraw-Hill, Inc., 1989, at pages 648-660, and the Kirk-Othmer Concise Encyclopedia of Chemical Technology, John Wiley & Sons, Inc. 1985, at pages 303-304 and 887-892.

1 encapsulated by the carrier. Encapsulation prevents the
2 pigment from reagglomerating, and thus results in excellent
3 pigment dispersion. The carrier of Example 1 hereinafter is
4 particularly effective for organic pigments, which tend to
5 be hydrophilic, because that carrier tends to drive off
6 moisture. With regard to the carrier of Example 1, the
7 isopropyl-tri-titanate reacts with the moisture in the
8 pigments and the stearamide to produce alcohol. The alcohol
9 acts as a catalyst with the stearamide to produce a crude
10 ester. The encapsulated ester extends the heat stability of
11 the pigment formula in addition to other chemicals present,
12 which also become encapsulated. It has been determined
13 through ageing studies that these granules are compatible
14 with most polymer systems.

15 The high-intensity mixer is run until the power
16 consumption drops to a level which indicates that the encap-
17 sulation process is complete. Granules, which are rounded,
18 spherelike particles, are formed by this process. The
19 granules are preferably about 10 microns to about 50 microns
20 in diameter, and more preferably about 10 microns to about
21 30 microns in diameter. These granules can include up to
22 about 90% pigment by weight. Processing the powdered pigment
23 and carrier through the high intensity mixer can increase
24 the bulk density of the mixture from about 1.75 times to
25 about 3.5 times.

26 A problem with these granules is that they are too
27 small for many purposes. They were not accepted in many
28 aspects of the commercial marketplace because they did not
29 have the size and shape of traditional extruded color concen-
30 trate pellets, and they tended to settle out when mixed and
31 processed with natural resin pellets and could not be used
32 effectively.

33 After the granules are formed in the high-intensity
34 mixer, they are cooled to room temperature.

1 A carrier is not necessarily a single compound;
2 combinations of ingredients can be utilized as a carrier,
3 which may also be referred to as a "carrier system." As
4 utilized in the illustrated embodiments, the components of
5 the carrier may have different melting points, but when
6 mixed, the mixture or carrier will melt at about 160° to
7 about 210° to about 220° F. The carrier has a melting point
8 less than about 230° F., preferably at about or less than
9 about 200° F. The color concentrate pellet, containing
10 pigment and carrier, will melt at about the same temperature
11 as that of the carrier of which it is formed. It is desir-
12 able that the carrier utilized be compatible with a wide
13 range of types of natural resin. When this is achieved, a
14 single type pellet can be utilized to color a variety of
15 different types of natural resins. In the conventional art,
16 as described above, a plurality of different types of pellets
17 of the same color are, or may be, needed to color the same
18 plurality of types of natural resin. The Examples hereinaf-
19 ter disclose carriers which are useful in the practice of the
20 present invention.

21 To make pellets in accordance with the present
22 invention, it is preferable to utilize a high intensity,
23 bowl-type mixer, such as is known in the art and is available
24 from the Henschel Company in Germany. This type mixer is
25 jacketed and hooked up to a cooling system. It has a large
26 rotary impeller that mixes and agitates the ingredients. The
27 pigment and carrier, both in powdered form, are placed in the
28 bowl without preheating. The mixer agitates and whips the
29 ingredients by means of the impeller. This action friction-
30 ally raises the temperature of the ingredients. Heat is thus
31 substantially mechanical rather than electrical or gas
32 combustion in origin. As the melting point is approached,
33 the carrier softens and agglomerates with the pigment parti-
34 cles. The pigment becomes wetted, ground, solvated, and

The granules are then processed through a pellet mill, such as Model CL type 3 from California Pellet Mill Company, 1114 East Wabash Avenue, Crawfordsville, Indiana 47933. This is a die-and-roller-type pellet mill. For an illustration of a die-and-roller-type pellet mill, see U.S. Pat. No. 4,080,134. In this pelletizing process, no external heat is added, substantial or otherwise. The temperature is not monitored and the pelleting is controlled by feed speed and volume only. The machine should be operated slowly enough so that the temperature is kept below the melting point of the carrier. Thus, the pellets are produced in a process, including high intensity mixing and pelletization, wherein the temperature does not exceed about 230° F., preferably not more than about 200° F.

With reference to FIG. 2, the color concentrate granules 20 are shown with respect to the die and rollers of the pellet mill. The pelleting process utilizes compaction and compression to produce the color concentrate pellets. The granules are fed continuously in a controlled, even stream from a supply hopper (not shown) to the pelleting cavity. The color concentrate granules 20 can be seen in the pelleting cavity. Rotation of the die 22 in contact with the rollers 24 causes the rollers 24 to turn. The granules carried by the rotation of the die 22 are compressed between the die 22 and the roller, and are forced through die cavities 26 in the die 22. As the color concentrate pellets 30 are extruded, a knife 28 shears the pellets. The length of the pellets can be controlled by controlling the process parameters. The die cavities are tubelike orifices, preferably circular in cross section, preferably without taper from inlet side to outlet side, and with a diameter between about 3/32 and about 5/32 inch, and preferably with a diameter of about 1/8 inch, so as to produce cylindrical pellets.

1 Alternatively, other cross sections, such as square, rectan-
2 gular, triangular, etc., can be utilized. The bulk density
3 of the pellets which come out of the pellet mill is approxi-
4 mately the same as the bulk density of the granules which go
5 into the pellet mill.

6 The pellets are "cold-pressed" or "cold-formed,"
7 which as used in the claims and specification herein means
8 mechanically pressed or compacted without applying substan-
9 tial external heat, and without melting the mass of the
10 material to form a cohesive and united body. When pellets
11 are formed in a pellet mill as described herein, the pellets
12 are friable. The granules are united by compaction. By cold
13 pressing the granules in the die cavities, the color concen-
14 trate pellets are shaped into forms that are mixable and
15 processable with conventionally shaped natural resin pellets
16 without substantial settling.

17 The pellets produced as described above are fria-
18 ble. They can be broken apart and/or crumbled with one's
19 fingernail, or with light tapping with the handle of a tool
20 such as a screwdriver. Since they are friable, these pellets
21 break up and incorporate more quickly with natural resin
22 pellets, thus leading to better mixing, dispersion and
23 distribution of the pigment throughout the natural resin.
24 Conventional extruded pellets tend not to be friable, but
25 tend to be a melted mass forming one body. The pellets of
26 the present invention are comprised of granules which have
27 not been melted and fused to form a single or continuous
28 body.

29 Organic pigments, being hydrophilic, will tend to
30 agglomerate if exposed to the atmosphere. The carriers of
31 the present invention tend to keep the organic pigments dry
32 when in pellet form.

33 Uniform dispersability is a desirable characteris-
34 tic in color concentrate pellets. The pellets of the present

1 invention have better dispersability and more uniform distri-
2 bution than conventional extruded pellets. This results in
3 more consistent color in part after part after part of the
4 ultimate product. Dispersability is measured in lightness,
5 chroma, and hue. The objective is to have the pigment
6 particles separated from one another, and evenly distributed
7 throughout the finished or final article. In the practice
8 of the present invention, lightness, chroma, and hue are put
9 under statistical process control, wherein these characteris-
10 tics are controlled to a 3-sigma control limit. Thus,
11 lightness, chroma, and hue are all controlled within 3-sigma
12 or less.

13 Most mixing and subsequent processing of color
14 concentrate pellets and natural resin pellets occurs at
15 temperatures up to and including about 400° F. Certain
16 pigments, including particularly organic pigments, are
17 degraded or burned out at 400° to 550° F. Such pigments
18 cannot generally be used in conventional extruded pellets,
19 since such pellets are produced at temperatures in the range
20 of 550° to 600° F. However, these heat-sensitive pigments
21 can be utilized in pellets of the present invention, since
22 such pellets are preferably produced at temperatures less
23 than about 200° F. and are then added to natural resins and
24 processed at temperatures not greater than about 400° F.

25 The color concentrate pellets of the present
26 invention can be used for injection molding (automobile and
27 non-automobile grades), sheet extrusion, profile extrusion,
28 casting, and blow molding. The pellets of the present
29 invention tend to be universal pellets in that they can be
30 used with a large number of different kinds of natural resin
31 pellets. This is in contradistinction to conventional
32 extruded pellets, which generally can be used only with
33 natural resin pellets which have a resin of the same or very
34 similar type as the carrier of the extruded pellet. The

1

14

2 universality of the pellets of the present invention is due both to the nature of the carrier
3 used and also to the fact that there can be so little carrier used per pellet. If there is only a
4 small amount of carrier in a pellet, it will tend not to affect the physical characteristics of
5 the finished product. For example, for 100 lbs. of natural resin, one may need only one
6 or two pounds of color concentrate pellets of the present invention. In addition, these
7 pellets melt more quickly, and thus blend better and are incorporated better with natural
8 resin pellets during the coloring process.

9 The Examples which follow illustrate the types of formulations which have been
10 successfully utilized to make color concentrate pellets according to the present invention.

11 EXAMPLE 1

12	Ingredient	Percent By Weight
13	Pigment	
14	titanium dioxide	25
15	carbon black	5
16	quinacridone red	22
17	quinacridone violet	20
18	cadmium yellow	3
19	Sorbitan monostearate	5
20	Titanate coupling agent (isopropyl- tri-titanate)	0.5
21	Ethylene bis stearamide (bis- stearamide wax)	19.5
22		

1

14a

2 In this Example, the last three ingredients comprise the carrier. The sorbitan
3 monostearate used is Glycomul S from Glyco Chemical Corp., Greenwich, Conn. It has a
4 melting point of 122° to 131° F. The titanate coupling agent used is Product TTS* from
5 Kennich Chemical Corp.

6 *denotes trade-mark

1

15

2 Bayonne, New Jersey 07002. The ethylene bis stearamide (bis stearamide wax) used is
3 Kemamide S* from Witco Chemical Company, Memphis, Tennessee. It has a melting
4 point of approximately 208°F. to 226° F. Thus, its melting point is between 120° and
5 250°F. Bis stearamide wax is also available from Glyco Chemical Corp., Greenwich,
6 Connecticut, as Acrawax C*. The monostearate acts as a surfactant; the titanate coupling
7 agent couples the pigment with the wetting agent; and the ethylene bis stearamide acts
8 as a wetting agent. In a pellet of this general composition, the ingredients can have
9 percent-by-weight ranges as follows: pigment, typically about 50% to about 75%; sorbitan
10 monostearate, 1% to 9%; titanate coupling agent, 0.5% to 1.0%; and bis stearamide wax,
11 15% to 45%.

12 The carrier of Example 1 is considered to be a universal carrier, and is compatible with a
13 very wide variety of natural resins, including ABS, polypropylene, high-density
14 polyethylene, low-density polyethylene, nylon, polycarbonate, polyvinyl chloride (flexible
15 and rigid), polyesters, acetals, and polystyrene. In the present invention, this universal
16 compatibility is due to the inherent compatibility of the carrier with the various natural
17 resins and/or because the carrier is present in such small amounts that it will not
18 appreciably affect the physical properties of the final product in which it is incorporated.
19 The carrier of Example 1 is a carrier frequently used with organic pigments because it
20 drives off the moisture which can be present in organic pigments (see the description
21 above).

22 A-C 6*, a low molecular weight polyethylene wax available from Allied Corporation,
23 Morristown, New Jersey, can be substituted for bis stearamide wax in this Example and
24 the other Examples herein. A-C 6* is particularly compatible with polystyrene, high
25 density polyethylene, and polypropylene.

26

* denotes a trade-mark

Products molded from a combination of pigment pellets of Example 1 and natural resin have an even, uniform distribution of pigment.

In the pigment of Example 1, molybdate orange, an inorganic pigment, can be substituted for the quinacridone red, an organic pigment. Alternatively, the organic pigments, in total, can be reduced in percentage to 1% or 5% and be replaced by titanium dioxide.

EXAMPLE 2

Ingredient	Percent By Weight
Pigment	
chroma yellow	80
quinacridone violet	20
phthalocyanine blue	10
Bis stearamide wax	5
A-C 400A* ethylene vinyl acetate (EVA)	5

The carrier in Example 2 is the last two ingredients. The ethylene vinyl acetate used is A-C 400A*, from Allied-Signal, Inc., Morristown, New Jersey A-C 400A* is an ethylene copolymer with vinyl acetate, comprising about 87% ethylene and about 13% vinyl acetate, and having a number average molecular weight of about 3000 and a melting point of about 203° F. It is believed that A-C 400A* with a vinyl acetate content of 12% to 16% would also work. A-C 400* is another alternative. It is believed that ethylene vinyl acetate with a melting point in the range of 190° to 220° F. and vinyl acetate content in the range of 12% to 16% would also work as an alternative to A-C 400A*. The ethylene in EVA causes good wetting with the pigment and subsequently causes good mixing with polyethylene, polypropylene, PVC, polystyrene, and similar natural resins, and has good compatibility across the conventional polymer range. The vinyl structure in EVA causes good mixing with vinyl-type resins such as PVC. The

* denotes a trade-mark

1 acetate in EVA causes good mixing with ABS and polystyrene
2 and similar-type resins. In Example 2, the ingredients can
3 range in percent-by-weight as follows: pigment, from about
4 50% to about 90%; bis stearamide wax, preferably from about
5 5% to about 30%; and ethylene vinyl acetate, preferably from
6 about 5% to about 30%. It is preferred that the bis-stea-
7 amide wax and the ethylene vinyl acetate be present in about
8 a 1:1 ratio by weight.

9 With a carrier of the type described in Example 2,
10 it is generally preferable to stay with a lower level of
11 organic pigments. Thus, alternatively, the quinacridone
12 violet can be eliminated and the phthalocyanine blue be
13 reduced in percentage to 1% or 5%, and chrome yellow be
14 increased to make up the difference. The organic pigments
15 do not work so well with this carrier, due to the fact that
16 organic pigments can contain moisture. The moisture can be
17 driven off; one simply has to run the Henschel mixer longer.
18 As can be seen, the carrier of Example 2 is suitable for
19 higher levels of pigment loading (i.e., up to about 90%,
20 including both organic and inorganic). In Example 2, the
21 pigment can also be all inorganic, such as 90% by weight
22 chrome yellow.

23 The carrier of Example 2 is compatible with all the
24 natural resins listed in Example 1. Thus, this carrier is
25 considered a universal carrier.

26 EXAMPLE 3

27	<u>Ingredient</u>	<u>Percent By Weight</u>
28	Pigment	
29	phthalocyanine green	40
30	quinacridone violet	2
31	titanium dioxide	38
32	Bis stearamide wax	10
33	A-C 400A ethylene vinyl acetate (EVA)	10

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☒ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.

1 In this composition, the pigment can range from
 2 about 40% to 60% to about 90% by weight, whereas, the remain-
 3 ing three ingredients combined can range from about 10% to
 4 about 60% by weight. Alternatively, the EVA can be elimi-
 5 nated, in which case the composition is 50% by weight pig-
 6 ment, 10% HALS, and 40% bis stearamide wax. Alternatively,
 7 in the formulation in the preceding sentence, ethylene vinyl
 8 acetate can be substituted for bis stearamide wax in some
 9 applications.

10 EXAMPLE 6

11	<u>Ingredient</u>	<u>Percent By Weight</u>
12	Pigment	
13	quinacridone red	30
14	quinacridone violet	5
15	azo yellow	7
16	titanium dioxide	4
17	carbon black	4
18	Hindered amine light stabilizer	
19	(HALS)	25
20	Carrier from Example 1	25

21
 22 Here, the carrier from Example 1 has three components, which
 23 are included in the same relative proportions as indicated
 24 in Example 1, to total 25% by weight. Pellets of this
 25 composition have been successfully tested.

1 The comments regarding Example 2 also apply to
2 Example 3.

EXAMPLE 4

<u>Ingredient</u>	<u>Percent By Weight</u>
Pigment	
quinacridone violet	25
phthalocyanine blue	17
titanium dioxide	25
carbon black	13
Hindered amine light stabilizer (HALS)	20

13 Pellets comprising the ingredients listed in
14 Example 4 have been prepared and have unique applicability.
15 HALS is an ultraviolet (UV) stabilizer and in this case acts
16 in a dual capacity, as the additive and as the carrier. HALS
17 is available from the Mitsui Company in Houston, Texas as
18 Product No. 770-LS. When pellets of this type are utilized
19 with natural resins, both pigment and a UV stabilizer are
20 added at the same time without the necessity of any other
21 carrier.

EXAMPLE 5

<u>Ingredient</u>	<u>Percent By Weight</u>
Pigment	
phthalocyanine green	25
azo yellow	17
carbon black	8
Hindered amine light stabilizer (HALS)	10
Bis stearamide wax	20
A-C 400A ethylene vinyl acetate (EVA)	20

20

EXAMPLE 7

Ingredient	Percent By Weight
Pigment	
titanium dioxide	20
phthalocyanine blue	10
nickel titanate yellow	5
copper chromite black	15
Bis stearamide wax	15
Siding-grade PVC compound	35

The carrier in Example 7 is specific for vinyl. Siding-grade PVC compound contains, on a by-weight basis, the following: 100 parts of Geon 101* EPF24* PVC resin from B.F. Goodrich Co., Cleveland, Ohio 44131; 0.4 to 2.5 parts tin stabilizer MT181* from Atochem North America, Buffalo, New York 14240; 1 to 2 parts Kemamide S* from Witco Chemical Co., Memphis, Tennessee; 0.5 to 2 parts COAD 10* calcium stearate from Maroon Chemical Co., Cleveland, Ohio; 0.1 to 0.5 parts Product K120N* process aid from Rohm & Haas Co., Philadelphia, Pennsylvania 19105; and 1 to 10 parts Richardson DS200* impact modifier from Nova Corp., Leominster, Massachusetts 10453. In Example 7, the pigment can range from about 20% to about 50% by weight, the bis stearamide wax can range from about 5% to about 20% by weight, and the PVC compound can range from about 20% to about 60% by weight. Alternatively, the pigment can be 100% inorganic.

From the foregoing, it can be seen that the carrier can be a mixture of a stearamide wax (bis stearamide) and a stearate (sorbitan monostearate) or a mixture of a stearamide wax and a low molecular weight, waxy EVA polymer. A waxy carrier has a substantial proportion of a waxy material or the equivalent of a waxy material, such as a low molecular weight EVA, for the described purposes. The carrier wets the pigment to facilitate proper dispersion in the natural resin. The carrier also assists in holding the pigment together in pellet form well enough to permit the pellets to be handled.

*denotes a trade-mark

1 reduces static electricity in the finished product. For
2 example, anti-stat pellets and color concentrate pellets
3 could be mixed and processed with natural resin pellets to
4 produce colored finished products with reduced static elec-
5 tricity properties.

6 EXAMPLE 10

7 Fillers

8 Various fillers can be substituted for pigment and
9 added to the carriers above and encapsulated and pelletized
10 as described. Such fillers would include calcium carbonate
11 (CaCO_3), talc, and glass. Calcium carbonate is available
12 from Palmer Supply Co., Cleveland, Ohio, and talc is avail-
13 able from Dartech Co., Cleveland, Ohio. It has been found
14 that when calcium carbonate is pelletized, as described, it
15 is much easier to handle and the clarity is much greater.

16 EXAMPLE 11

17 UV Light Stabilizers

18 Ultraviolet (UV) light stabilizers such as HALS
19 from Mitsui Company in Houston, Texas can be substituted for
20 pigment and treated like the fillers, anti-stat, and slip
21 agents described above. They have been demonstrated to work
22 very well in the field.

23 It has also been discovered that powdered or flaked
24 HALS can be run through a pellet mill and pelletized, without
25 first processing it in a Henschel mixer, to produce pellets
26 which are 100% HALS. No pigments, carriers, or additives are
27 added. These pellets are expected to be very useful in the
28 automotive industry.

h/c
2/28/91

1 but not so much as to prevent friability. The carrier also
2 tends to hold the granules together. As noted, however, the
3 pellets are friable and easily broken apart, all of which is
4 an advantage in the mixing process.

5 The present application also has application beyond
6 organic and inorganic pigments. Based on experimental
7 evidence to date, certain other materials in the nature of
8 fillers and additives can be substituted for the pigment in
9 the above Examples, and be bound by the carriers identified
10 in the above Examples and be encapsulated in the high inten-
11 sity mixer and pelletized as described above to form pellets
12 which are mixable and processable with conventionally sized
13 natural resin pellets without settling out (substantial or
14 otherwise). This will make the use of these fillers and
15 additives much more convenient and effective in the plastics
16 industry. The following Examples are given to illustrate
17 this invention.

18 EXAMPLE 8

19 Slip Agents

20 Bis stearamide wax can be substituted for pigment
21 and added to the carriers above as a slip agent. A slip
22 agent reduces static electricity and lets sheets of molded
23 material slide apart so that they will not stick together.

24 EXAMPLE 9

25 Anti-Stats

26 MOLD-WIZ, a trademark of Axel Plastics Company,
27 Woodside, New York, can be substituted for pigment and added
28 to the carriers above as an anti-stat. Such a component

Handwritten:
H. J.
2/28/51

THE EMBODIMENTS OF THE INVENTION IN WHICH AN EXCLUSIVE PROPERTY OR PRIVILEGE IS CLAIMED ARE DEFINED AS FOLLOWS:

1. A color concentrate pellet comprising at least about 30% pigment by weight and a carrier wherein said color concentrate pellet has at least partially a geometric shape formed by a die cavity and is of a size and shape and composition such that a plurality of said color concentrate pellets are mixable and processable with commercially sized natural resin pellets to produce coloured resin without substantial settling out of said color concentrate pellets from said natural resin pellets, the carrier of said color concentrate pellet operating to bind the pigment, and wet the pigment to render it more dispersible in said natural resin, and having a melting point less than about 230°F, said pellet being cold-formed in a press in such a way that the pellet is cohesive as a result of mechanical pressure and is friable to improve its dispersibility.
2. The color concentrate pellet of claim 1, wherein said carrier comprises a wax with a melting point between 120°F and 250°F.
3. The color concentrate pellet of claim 2, wherein said wax is bis stearamide wax.
4. The color concentrate pellet of claim 1, wherein said color concentrate pellet comprises at least 80% pigment by weight.
5. The color concentrate pellet of claim 1, wherein said color concentrate pellet comprises at least 45% by weight of inorganic pigments and at least 1% by weight of organic pigments.
6. A pellet for use in the plastics industry, comprising a carrier and an additive, said additive being selected from the group consisting of a slip agent, an anti-stat compound, calcium carbonate, talc, glass, ultraviolet light stabilizer and purging compound, wherein said pellet has at least partially a geometric shape formed by a die cavity and is of a size and shape such that a plurality of said pellets are mixable and processable with commercially sized natural resin pellets without substantial settling out of said pellets from said natural resin pellets, said carrier operating to bind the pigment, and wet the pigment to render it more dispersible in said natural resin, and having a melting point of less than about 230°F, said pellet being cold-formed in a press in such a way that the pellet is cohesive as a result of mechanical pressure.

7. The color concentrate pellet of claim 1, said plurality of said pellets being commercially mixable and processable and compatible with polypropylene, high-density polyethylene, and polystyrene natural resin pellets.

5 8. The color concentrate pellet of claim 1, said plurality of said pellets being commercially mixable and processable and compatible with polypropylene, high-density polyethylene, polystyrene, acrylonitrile-butadiene-styrene, low-density polyethylene, and polyvinyl chloride natural resin pellets.

9. The color concentrate pellet of claim 1, the carrier comprising an ultraviolet light stabilizer.

10 10. The color concentrate pellet of claim 9, wherein said ultraviolet light stabilizer is a hindered amine light stabilizer.

11. The color concentrate pellet of claim 1, the carrier consisting of an ultraviolet light stabilizer.

15 12. A color concentrate pellet comprising at least 20% pigment by weight and a carrier wherein said color concentrate pellet has at least partially a geometric shape formed by a die cavity and is of a size and shape and composition such that a plurality of said color concentrate pellets are mixable and processable with commercially sized natural resin pellets to produce colored resin without substantial settling out of said color concentrate pellets from said natural resin pellets, the carrier of said color concentrate pellet operating to bind the pigment, and wet the pigment to render it more dispersible in said natural resin, and
20 having a melting point less than about 230°F, said pellet being cold-formed in a press in such a way that the pellet is cohesive as a result of mechanical pressure and is friable to improve its dispersibility, said carrier comprising siding-grade polyvinyl chloride compound.

13. The pellet of claim 6, said additive being a slip agent.

14. The pellet of claim 6, said additive being an anti-stat compound.

25 15. The pellet of claim 6, said additive being calcium carbonate.

16. The pellet of claim 6, said additive being talc.

17. The pellet of claim 6, said additive being glass.

EXAMPLE 12Purging Compounds

Purging compounds can be encapsulated in the Henschel mixer and pelletized in the pellet mill as described above. A typical purging compound is 10% titanium dioxide, 60% calcium carbonate, 10% antimony oxide, and 20% bis stearamide wax. Such purging compound pellets have been demonstrated to work very well in the field. A purging compound is used basically to clean old pigment and plastic out of a machine. A purging compound is a highly loaded compound containing abrasive materials that scours out the previous residue.

It will be clear to those skilled in the art that various modifications and changes can be incorporated in the aspects of the present invention. All such modifications and changes that fall within the scope of the appended claims are intended to be covered by the present application.

18. The pellet of claim 6, said additive being an ultraviolet light stabilizer.
19. The pellet of claim 6, wherein said carrier and said additive are both 100% hindered amine light stabilizer.
20. The pellet of claim 6, said additive being a purging compound.
5. 21. The pellet of claim 6, said plurality of said pellets being commercially mixable and processable and compatible with polypropylene, high-density polyethylene, and polystyrene natural resin pellets.
10. 22. The pellet of claim 6, said plurality of said pellets being commercially mixable and processable and compatible with polypropylene, high-density polyethylene, polystyrene, acrylonitrile-butadiene-styrene, low-density polyethylene, and polyvinyl chloride natural resin pellets.
23. The pellet of claim 6, the carrier comprising an ultraviolet light stabilizer.
24. The pellet of claim 23, wherein said ultraviolet light stabilizer is a hindered amine light stabilizer.
15. 25. The pellet of claim 6, the carrier consisting of an ultraviolet light stabilizer.
26. The color concentrate pellet of claim 7, said carrier comprising bis stearamide wax and ethylene vinyl acetate.
20. 27. The color concentrate pellet of claim 26, said pellet having a cylindrical shape formed by a circular die cavity, said pellet comprising about 5% to about 30% bis stearamide wax by weight, about 5% to about 30% ethylene vinyl acetate by weight, and about 50% to about 90% pigment by weight.
28. The color concentrate pellet of claim 27, the bis stearamide wax and ethylene vinyl acetate being present in about a 1:1 ratio by weight, the pellet comprising at least 1% organic pigment by weight.
25. 29. The color concentrate pellet of claim 1, said color concentrate pellet further comprising about 10% to about 25% hindered amine light stabilizer by weight and about 50% to about 80% pigment by weight.

30. The color concentrate pellet of claim 11, said ultraviolet light stabilizer being hindered amine light stabilizer, said color concentrate pellet comprising about 20% hindered amine light stabilizer by weight and about 80% pigment by weight.

5 31. The color concentrate pellet of any one of claims 1 to 5, wherein said color concentrate pellet comprises 60% to 90% pigment by weight.

32. The color concentrate pellet of any one of claims 1 to 5, wherein said color concentrate pellet comprises 70% to 90% pigment by weight.

33. The color concentrate pellet of any one of claims 1 to 5, wherein said color concentrate pellet comprises 80% to 90% pigment by weight.

10 34. The color concentrate pellet of any one of claims 1 to 5, wherein said carrier has a melting point of about 160°F to about 220°F.

35. The color concentrate pellet of any one of claims 1 to 5, wherein said carrier has a melting point of about 160°F to 210°F.

15 36. The color concentrate pellet of any one of claims 1 to 5, wherein said carrier has a melting point of about 200°F.

37. The color concentrate pellet of any one of claims 1 to 5, wherein said carrier comprises a wax with a melting point of approximately 208°F to 226°F.

38. The pellet of claim 6, said additive being calcium carbonate, said pellet comprising 60% to 90% calcium carbonate by weight.

2037603




Fig. 1




Fig. 2

Alex. E. MacRae & Co.

